

# Christy<sup>®</sup> Pak Ceramic Raschig Rings

## FEATURES

- High mechanical strength
- Economical
- High available surface area
- Well-proven in thousands of installations worldwide



## PACKING DATA

Nominal Diameter	Density	Surface Area	Free Space	Wall Thickness*
in (mm)	lb/ft <sup>3</sup> (kg/m <sup>3</sup> )	Ft <sup>2</sup> /ft <sup>3</sup> (m <sup>2</sup> /m <sup>3</sup> )	(%)	in (mm)
¼ (6)	55.56 (890)	283 (930)	58	0.08 (2.0)
¾ (19)	45.20 (724)	240 (787)	72	0.15 (3.8)
1 (25)	38.71 (620)	58 (190)	72	0.10 (3.0)
1.5 (38)	36.21 (580)	46 (150)	76	0.16 (4.0)
2 (50)	33.71 (540)	29 (93)	77	0.20 (5.0)
3 (76)	33.4 (535)	19 (65)	78	0.40 (9.5)
4 (100)	32.46 (520)	18 (60)	80	0.40 (10.0)

\*Note: The wall thickness shown in the table above is the standard thickness for each size. Different wall thickness is also available.

Christy Catalytics, LLC offers a complete range of catalyst bed supports, tower packings and tower internals.

THE ABOVE DATA ARE BASED ON CONTROLLED TESTING. INDIVIDUAL TEST RESULTS MAY VARY; THEREFORE THESE DATA MAY NOT BE USED FOR SPECIFICATION PURPOSES.

NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, ARE MADE REGARDING THE DATA OR PRODUCTS SHOWN ABOVE.

Revised: November 2019